# Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/008458

International filing date: 15 March 2005 (15.03.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US Number: 60/553.659

Filing date: 16 March 2004 (16.03.2004)

Date of receipt at the International Bureau: 18 April 2005 (18.04.2005)

Remark: Priority document submitted or transmitted to the International Bureau in

compliance with Rule 17.1(a) or (b)





## THE INTERED STATES OF ANTER OF

TO ALL TO WIGH THISE, PRESENTS, SHAME COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

April 07, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

> APPLICATION NUMBER: 60/553.659 FILING DATE: March 16, 2004

RELATED PCT APPLICATION NUMBER: PCT/US05/08458

Certified by

Under Secretary of Commerce for Intellectual Property and Director of the United States Patent and Trademark Office

=	
	-
=	
≣.	
₫.	
=	

Respectfully submitted

SIGNATURE \_

PTOSB/16 (08-03)
Approved for use through 07/31/2006, 09(08-03)
U.S. Patent and Trademan Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of increasing under the September a vertical former number.

#### PROVISIONAL APPLICATION FOR PATENT COVER SHEET This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

	L APPLICATI						U.S. PT
Express Mail Label No	D. ET122668029US						. 4
D EXPICES MAIN ESSENTES	11	VENTOR(S	5)				79
Given Name (first and middle [if an						sidence late or Foreign Country)	22264
Dany Norwin							
Additional inventors are being	g named on thi sepai	rately number	ed sheets att	ached h	ereto		
METHOD FOR PREPARING LONG	TITLE OF THE IN GLASS FIBER-REINFOR				ICATED	ARTICLES THEREFROM	
Direct all correspondence to:	CORRESP	ONDENCE A	DDRESS		-		
Customer Number	33101						
Firm or Individual Name							
Address							
Address							
City		State			ZIP		
Country		Telephone			Fax		
	ENCLOSED APPLICAT	ION PARTS	(check all th	at apply	)		
Specification Number of Pag	ges 16		CD(s), N	umber			
Drawing(s) Number of Sheets  Other (specify)  Application Data Sheet. See 37 CFR 1.76							
METHOD OF PAYMENT OF FILING	G FEES FOR THIS PROV	VISIONAL AF	PLICATION I	FOR PA	TENT		$\neg$
Applicant claims small entit  A check or money order is  The Director is hereby auth fees or credit any overpaym Payment by credit card. For	ty status. See 37 CFR 1.2 enclosed to cover the filin prized to charge filing nent to Deposit Account N	7. g fees lumber				FILING FEE AMOUNT (\$) \$160.00	
The invention was made by an ager United States Government.  No.				tract wit	h an age	ncy of the	

(if appropriate) TYPED or PRINTED NAME Michael A. Schaldenbrand 25289-0025 Docket Number: (248) 433-7570 TELEPHONE -

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT
This collection of information is required by 37 CFR 1.51. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentially is gowered by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the completed application to the USPTO. Time will viary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing the burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 2313-1450, DO NOT SEND FESS OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Mail Stop Provided Application,

03/16/04

REGISTRATION NO.

47,923

PTOISB17 (10-03)
Approved for use through 07/31/2006. OMB 0851-0032
Patent and Trademank Office: U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Complete if Vocum

FEE IRANSWILLIAL								
		Application Number			ber			
for FY 2004	L	Filing Date						
Effective 10/01/2003. Patent fees are subject to annual revi	sion.	First Named Inventor			entor	Dany De Kock		
Applicant claims small entity status. See 37 CFR 1	.27	Examiner Name						
<del></del>		Art Unit						
TOTAL AMOUNT OF PAYMENT   x>s \$10	50.00	0.00 Attorney Docket No.			No.	25289-0025		
	-	_	÷		_			
METHOD OF PAYMENT (check all that apply)	_			FE	E C	ALCULATION (co	intinued)	
Check Credit card Order Other None			DNAL					
Deposit Account:	Fee	Entity Fee	Fee	Entity Fee	L	Fee Description		Fee Paid
Deposit Account 04-1061	Code	(\$)	Code 2051	(\$)	Curch	large - late filing fee or		reeraid
Account Number 04-1061	1051					large - late provisional		=
Deposit Account Dickinson Wright PLLC	1052	50	2052	25	sheet			
Account Name Dickinson Wright PLLC	1053	130	1053	130	Non -	English specification		
The Director is authorized to: (check all that apply)	1812	2,520	1812	2,520	For fil	ing a request for ex pa	arte reexamination	
Charge fee(s) indicated below Credit any overpayments	1804	920*	1804	920*	Requi	esting publication of S	IR prior to Examiner	
Charge any additional fee(s) or any underpayment of fee(s)	1805	1.840*	1805	1.840*		i esting publication of S	IR after Examiner	=
Charge fee(s) indicated below, except for the filling fee					action			
to the above-identified deposit account.	1251	110	2251			sion for reply within fir		
FEE CALCULATION	1252		2252			sion for reply within se		
1. BASIC FILING FEE	1253		2253			sion for reply within th		
Large Entity   Small Entity		1,480	2254			sion for reply within fo		
Fee Fee Fee Fee Description Code (\$) Code (\$) Fee Paid	1255	2,010	2255	.,		sion for reply within fif	th month	
1001 770 2001 385 Utility filing fee	1401	330	2401			of Appeal		
1002 340 2002 170 Design filing fee	1402	330	2402		-	a brief in support of a	n appeal	
1003 530 2003 285 Plant filing fee	1403	290	2403			est for oral hearing		
1004 770 2004 385 Reissue filing fee	1451	1,510	1451			on to institute a public		
1005 160 2005 80 Provisional filing fee 160.00	1452	110	2452			on to revive - unavoida		
SUBTOTAL (1) 2 > 5 \$160.00	1453	1,330	2453	665	Petitic	on to revive - unintenti	onal	
2. EXTRA CLAIM FEES FOR UTILITY AND	1501	1,330	2501	665	Utility	issue fee (or reissue)		
Fee from	1502	480	2502	240	Desig	n issue fee		
Extra Claims below Fee Paid	1503	640	2503	320	Plant	issue fee		
Total Claims		130	1460	130	Petitic	ons to the Commission	ner	
Ctaims Multiple Dependent	1807	50	1807	50	Proce	ssing fee under 37 CF	R § 1.17(q)	
Larne Entity   Small Entity	1806	180	1806	180	Subm	ission of Information C	Disclosure	
Fee Fee Fee Fee Description Code (\$) Code (\$)	8021	40	8021	40	Recor	ment rding each patent assi number of properties	gnment per property	
1202 18 2202 9 Claims in excess of 20 1201 86 2201 43 Independent claims in excess of 3	1809	770	2809	385	Filing	a submission after fin. FR § 1.129(a))		
1203 260 2203 145 Multiple dependent claims if excess of 3	1810	770	2810	385		ech additional invention	n to be examined	
1204 86 2204 43 "Reissue independent claims	1801	770	2801	385		est for Continued Exar	mination (RCE)	
over original patent	1802	900	1802	900	Reque	est for expedited exam	nination	$\overline{}$
1205 18 2205 9 "Reissue claims in excess of 20 and over original patent	Oth	er fee (	specify		of a d	esign application		
SUBTOTAL (2) x>5 \$0.00								
"or number previously paid, if greater; For Reissues, see above "Reduced by Basic Filling Fee Feild SUBTICTAL (3) x>s								
SUBMITTED BY Complete (# applicable)								
Name (Print/Type) Michael A. Schaldenbrand		Registr	ation No (Apent)	).	47,5		(248) 433-	7570
Signature M. A. LAUALAMAAA	hr	TT				Date	March 16, 20	104

M.a alundadami WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on

This collection of information is required by 37 CFR 117 and 11.27. The information is required to obtain or retain a benefit by the public which is to fit (and by the USPTO) to process) an application. Confidentially is governed by \$1.00. The 2 and \$1.00. The confidential by the public which is to fit (and by the USPTO) to process) an application. Confidentially is governed by \$1.00. The 2 and \$1.00. The Confidential by the Confidential by the Confidential by the Confidential Conf

			·			
CERTIFICATE OF I	MAIL" (37 CFR 1.10)	Docket No. 25289-0025				
Serial No. Filing Date Examiner Group Ar						
	OR PREPARING LONG GLASS THEREFROM	FIBER-REINFORCED COMPO	OSITION AND FABRICATED			
	following correspondence:					
PROVISIONAL PATE Provisional Application page provisional patent		Fee Transmittal for FY 2004 (1 p	34549 for \$160.00, page, in duplicate) and 16			
		of correspondence)				
is being deposited with	the United States Postal Service	e "Express Mail Post Office to A	Addressee" service under 37			
CFR 1.10 in an envelo	pe addressed to: Commissioner	for Patents, P.O. Box 1450, Ale	xandria, VA 22313-1450 on			
	March 16, 2004 (Date)					
		Tina Tomay				
(Typed or Printed Name of Person Mailing Correspondence)						
(Signande of Person Walling Correspondence)						
ET122668029US						
("Express Mail" Mailing Label Number)						
	Note: Each paper must ha	ve its own certificate of mailing.				

# METHOD FOR PREPARING LONG GLASS FIBER-REINFORCED COMPOSITION AND FABRICATED ARTICLES THEREFROM

## FIELD OF THE INVENTION

The present invention concerns a process for preparing a long fiber glass-filled thermoplastic composition and fabricated articles therefrom.

#### BACKGROUND OF THE INVENTION

It is well known that the physical properties of thermoplastics can be improved by the incorporation of filler materials such as glass fibers. The incorporation of reinforcing fibers into polymeric products beneficially affects resin properties such as tensile strength, stiffness, dimensional stability and resistance to creep and thermal expansion. Traditional methods of producing such articles have been through use in standard, pre-compounded short fiber glass-filled ABS. While satisfying certain objectives in optimizing the quality of the finished product, conventional methods have proven to be commercially costly and in other ways have fallen short of their objectives in terms of density, impact performance and strength. A lower cost solution to the known methods of producing fiber-reinforced articles is desired.

Certain steps have been taken in overcoming the deficiencies of known methods by incorporating long glass fibers into thermoplastic material for producing a long fiber-reinforced thermoplastic article. In this regard reference may be had to WO 01/02471, titled LONG FIBER-REINFORCED THERMOPLASTIC MATERIAL AND METHOD FOR PRODUCING THE SAME. According to this reference, long glass fibers are impregnated with a first thermoplastic material. The matrix of the material is composed of at least two different thermoplastics, thus enabling the fibers to be wet by one of the two thermoplastic materials. The resulting article demonstrates improved physical, chemical and electrochemical properties. However, while demonstrating an improvement in the state of technology, the process set forth in WO 01/02471 is

burdened by the requirement to employ at least two thermoplastics for production of the class fiber reinforced granulate.

Reference may also be had to WO 0003852, titled GRANULES FOR THE PRODUCTION OF A MOLDING WITH A CLASS-A SURFACE, PROCESS FOR THE PRODUCTION OF GRANULES AND ITS USE. According to this reference, a granulate for the production of Class-A surface moldings is provided. The granulate comprises a thermoplastic polymer and long fiber material. The fiber material is provided with lengths in the range of 1 to 25 mm. While also demonstrating an improvement in the state of technology, this reference is limited in its application to articles requiring Class-A surfaces and, furthermore, is limited by its inherent inability to achieve performance benefits realized through the use of amorphous polymers.

Further reference may be made to U.S. Patent No. 5,783,129, titled APPARATUS, METHOD, AND COATING DIE FOR PRODUCING LONG FIBER-REINFORCED THERMOPLASTIC RESIN COMPOSITION. According to this reference a method is disclosed for producing a long fiber-reinforced thermoplastic resin composition composed of a thermoplastic resin and fiber bundles. The preferred resins are selected from the group which includes semi-crystalline polymers like polyolefins, polyesters, and polyamides. A reference to the same assignee, U.S. Patent No. 5,788,908 for METHOD FOR PRODUCING FIBER-REINFORCED THERMOPLASTIC RESIN COMPOSITION, is similar in that it too discloses a method for producing long fiber-reinforced thermoplastic resin composition. According to the disclosed method of production, a web-like continuous fiber bundle is impregnated with a thermoplastic resin melt to form a composite material. As with the preceding reference, the preferred resins

are selected from the group which includes semi-crystalline polymers like polyolefins, polyesters, and polyamides. While these methods provide certain advantages over the prior art, the products produced by these methods are not able to demonstrate desired dimensional performance.

It would therefore be desirable to find an efficient and effective means of producing long glass fiber-reinforced articles that demonstrate lowered density, improved impact properties, improved strength properties, and superior dimensional stability as achieved with amorphous polymers but at reduced production costs.

#### SUMMARY OF THE INVENTION

The present invention addresses the deficiencies of the art by providing a process for preparing a superior long glass fiber-reinforced composition for the production of a glass fiber-reinforced article of manufacture generally comprising:

- (a) Selecting a quantity of long glass fiber;
- (b) adding the selected quantity of long glass fiber to a first copolymer to form a master-batch, the first copolymer being a high flow copolymer; and
- (c) blending the master-batch with a second copolymer, the second copolymer being a stiffer flowing amorphous styrenic copolymer.

The first copolymer, the high flow copolymer, is preferably styrene-acrylonitrile (SAN), although others polymers may be used in addition to or in lieu thereof when forming a homogeneous blend with the stiffer flowing amorphous styrenic copolymer. The second copolymer, the stiffer flowing styrenic copolymer, is acrylonitrile-butadiene-styrene (ABS), although others may be used in addition to or in lieu thereof. The master-batch is preferably dry-blended or is dosed by the use of a mixing unit with the second styrenic copolymer.

#### DETAILED DESCRIPTION OF THE INVENTION

The present invention provides a process for the preparation of a superior long fiber glass-filled thermoplastic composition for use in the production of a molded article that demonstrates high dimensional stability. The method for producing the composition of the present invention offers a low-cost approach to the production of a moldable compound having low density and high impact strength when compared to products produced by known methods.

The process of the present invention for the preparation of a fiber-reinforced product comprises the general steps of selecting a quantity of long glass fiber, adding the selected quantity of long glass fiber to a high flow of a first copolymer to form a master-batch, blending the master-batch with a second stiffer flowing styrenic copolymer to form an injection moldable or compression moldable glass fiber-reinforced resin compound, injecting the resin compound into a mold, and recovering a fiber-reinforced polymerized part.

The targeted fiber length in the master-batch is between 3.0 mm and 25.0 mm with an average length of about 15.0 mm. Long glass fibers or a plurality of glass strands bundled in the form of widely-used glass roving may be incorporated. Specific glass rovings may be used for particular applications. In any event, typically the glass fibers will be substantially uniform in length, with the length dependent upon the granule size of the long glass fiber master-batch.

The targeted average fiber length in the final product is between 0.5 mm and 25.0 mm with a preferred average length between 3.0 mm and 8.0 mm when injected molded. In the event that the pellets are compression molded, the fiber length will be

related to the size of the pellets, e.g., the fiber length would be between 11.0 mm and 25.0 mm.

The glass fibers are added to a flow of a carrier melt. The carrier is a high flow copolymer which provides sufficient wetting and reduced shear forces on the glass fibers to avoid uncontrolled sizing but sufficient dispersion. The carrier material is a high flow version of, or forms a homogenous mixture with, the second stiffer flowing unreinforced amorphous unfilled material. The carrier may consist of both amorphous or functionalized semi-crystalline materials or blends thereof. Preferably the carrier is a styrene-acrylonitrile (SAN) such as Tyril ® (trademark, Dow Chemical Company) or acrylonitrile-butadiene-styrene (ABS) such as MAGNUM ® (trademark, Dow Chemical Company) or a styrene-maleic anhydride (SMA) such as DYLARC ® (trademark, Arco Chemical Company). As a variation to the use of a styrenic-based carrier, alternate high flow versions engineering thermoplastic resins may be used or blended with the styrenic-based carrier such as polycarbonate (PC) such as CALIBRE ® (trademark, Dow Chemical Company) or a thermoplastic polyurethane such as ISOPLAST ® (trademark, Dow Chemical Company).

Although there are alternative methods for adding the glass fibers to the carrier flow, the glass fiber may be added to the high flow carrier melt by way of a side feeder of the compounding unit. Preferably the glass fiber is added to the high flow carrier melt in such an amount so that sufficient wetting and dispersion is achievable. A glass fiber concentration of 75% is possible but may provide a high vulnerability to poor dispersion. Preferably the glass fiber concentration is in the range of between about 40% and 60%

with the overall objective being to provide as high a concentration as possible while minimizing poor dispersion.

Once the master-batch is formed it is dry-blended with the stiffer flowing unreinforced, second amorphous copolymer. Preferably the second unreinforced amorphous material is a styrenic copolymer such as an acrylate styrene acrylonitrile (ASA), ABS, or SMA. This neat polymer will contribute to the strength and heat of the final blend. By use of the master-batch concept, the high level performance of the second polymer is not compromised with additional material characteristics as required for a high dosing level LG fiber reinforcing process.

The addition level of the master-batch is between about 10% and about 40% depending on the required stiffness and dimensional performance of the final article.

The resulting dry blend is injected molded under standard injection conditions for the second non-reinforced polymer into a mold. The resulting glass fiber-reinforced article is thereafter removed from the mold.

A broad variety of additives may be included in the thermoplastic resins set forth above according to the specific applications and use of the resin composition. Such additives may include one or more of colorants, de-molding agents, anti-oxidants, UV stabilizers or inorganic fillers

In general, a fiber-reinforced molded article produced according to the method fo the present invention achieved several unexpected results. Of these results it was found that fewer glass fibers were needed to obtain a similar heat performance when compared with articles prepared according to known methods. It was also found that the resulting article had lower density and reduced weight when compared with such

articles. Furthermore, the resulting article demonstrated improved impact performance, strength levels and heat resistance (at equivalent levels of stiffness) over articles produced according to known methods.

The process of the present invention is illustrated by the following practical example and comparative testing wherein all parts and percentages are by volume unless otherwise specified.

#### PRACTICAL EXAMPLE

A long glass fiber master-batch is prepared using glass roving added, via a pultrusion or co-extrusion process, into a high flow SAN melt. The obtained glass fiber content in the master-batch was between 55% and 60%. This master-batch was dryblended with several neat mass ABS resins in blending ratios between 15% and 35%. The dry-blend was used for molding articles in an injection molding machine under standard ABS conditions into an ISO test specimen.

#### COMPARATIVE TESTING

The table below shows the obtained physical properties for three different dry blends prepared in accordance with the practical example set forth above with the exception of specified variations in glass levels in the master-batch and targeted glass fiber levels. Comparisons were made with a commercially available 16% short glass fiber containing ABS (Reference 1) compound and a commercially available 17% short glass fiber containing ABS (Reference 2).

	Load	neat ABS grade	Sample 1 MAGNUM® 3404	Sample 2 MAGNUM® 3404	Sample 3 MAGNUM® 3416	Reference 1	Reference 2
Norm	Unit	Addition IVI LFG MB	26%	35%	30%	0	0
		Targeted Glass IvI	15%	20%	17%	16%	17%
	kg/l	Density	1.145	1.191	1.16	1.16	1.17
	%	ash content	13.8	19	16	16	
ISO 178	MPa	Flex.mod.(regr.0.05- 0.25%)	5279	5910	6201	5519	4700
ISO 178	MPa	Flex strength	· 134	145	150	103	90
ISO 527-2	MPa	Tensile yield	88	99	99	74	65
ISO 527-2	%	Elongation at rupture	2.3	1.9	2.1	1.7	
ISO 527-2	MPa	Regr. modulus (0.05- 0.25%)	4810	6200	5857	5575	5100
ISO 179/1f	kJ/m²	Unnotched Charpy impact 23°C	23.2	22.8	24.5	18	
ISO 179/1e	kJ/m²	Notched Izod impact 23*C	14.2	14.6	14.2	6	7
ISO 75A	*C	HDT 1.8MPa	104	119	109	102	96
ISO 306	°C	Vicat 50°C/hr 5kg	106	110	113	106	101
ISO6603-2	J	Total energy	8.5	8.8	8.2	4.6	

<sup>&</sup>quot;Magnum" is a registered trademark of the Dow Chemical Company.

As the comparative results illustrate, the articles produced according to the composition and method of the present invention demonstrate superior qualities in several areas, including reduced density, increased modulus, increased strength, improved notched impact strength and practical toughness and improved heat resistance.

It is understood that the above are merely preferred embodiments and that various changes and alterations can be made without departing from the spirit and broader aspects of the invention.

#### CLAIMS

What is claimed is:

 A method for producing a long glass fiber-reinforced thermoplastic resin composition, the method comprising the steps of:

selecting a quantity of long glass fiber;

adding the selected quantity of long glass fiber to a first copolymer to form a master-batch, said first copolymer being a high flow copolymer; and

blending the master-batch with a second copolymer.

- The method in accordance with Claim 1 wherein the first and second copolymers are styrenic copolymers.
- The method in accordance with Claim 1 wherein the first copolymer is selected from the group consisting of styrene-acrylonitrile (SAN), acrylonitrile-butadienestyrene (ABS), and an alloy of ABS resins.
- 4. The method in accordance with Claim 1 wherein the second copolymer is a stiffer flowing material selected from the group consisting of acrylonitrile-butadienestyrene (ABS), styrene-maleic anhydride (SMA), acrylate styrene acrylonitrile (ASA), and alloys thereof.

- The method in accordance with Claim 1 wherein the second copolymer is a stiffer flowing material and blends with the first copolymer to form a homogeneous blend.
- The method in accordance with Claim 1 wherein the second copolymer is a stiffer flowing amorphous styrenic copolymer.
- The method in accordance with Claim 1 wherein the selected quantity of glass fibers is added to a high flow of the first copolymer.
- 8. The method in accordance with Claim 1 wherein the selected quantity of glass fibers is added to the first copolymer in such an amount so that the resulting master-batch has a glass fiber concentration of between about 40% and 75%.
- The method in accordance with Claim 1 wherein the blending ratio of the master-batch with the second copolymer is between about 10% and about 40%.
- The method in accordance with Claim 1 wherein the long glass fiber is glass roving.
- The method in accordance with Claim 1 wherein the master-batch is dryblended with the second copolymer.

	12.	The method in accordance with Claim 1 wherein the second copolymer is $ \\$
a nea	mass	acrylonitrile-butadiene-styrene (ABS) resin.

13. A method for producing a long glass fiber-reinforced thermoplastic resin composition, the method comprising the steps of:

selecting a quantity of long glass fiber;

adding the selected quantity of long glass fiber to a first copolymer to form a master-batch, the first copolymer being selected from the group consisting of styrene-acrylonitrile (SAN), acrylonitrile-butadiene-styrene (ABS), an alloy of ABS resins, and polycarbonate; and

dry blending the master-batch with a second copolymer selected from the group consisting of acrylonitrile-butadiene-styrene (ABS), styrene-maleic anhydride (SMA), acrylate styrene acrylonitrile (ASA), and alloys thereof.

- The method in accordance with Claim 13 wherein the first copolymer is a high flow copolymer.
- 15. The method in accordance with Claim 13 wherein the second copolymer is a stiffer flowing material and blends with the first copolymer to form a homogeneous blend.
- 16. The method in accordance with Claim 13 wherein the selected quantity of glass fibers is added to a high flow of the first copolymer.

- 17. The method in accordance with Claim 13 wherein the selected quantity of glass fibers is added to the first copolymer in such an amount so that the resulting master-batch has a glass fiber concentration of between about 40% and about 75%.
- 18. The method in accordance with Claim 13 wherein the blending ratio of the master-batch with the second copolymer is between about 10% and about 40%.
- The method in accordance with Claim 13 wherein the long glass fiber is glass roving.
- 20. A glass fiber-reinforced article manufactured by the process comprising: adding a quantity of long glass fiber to a first copolymer to form a master-batch, the first copolymer being a high flow copolymer selected from the group consisting of styrene-acrylonitrile (SAN), acrylonitrile-butadiene-styrene (ABS), an alloy of ABS resins, and polycarbonate;

blending the master-batch with a second copolymer selected from the group consisting of acrylonitrile-butadiene-styrene (ABS), styrene-maleic anhydride (SMA), acrylate styrene acrylonitrile (ASA), and alloys thereof to form an injectable composition; and

injecting the composition into a mold.

### ABSTRACT

Process for production of a long fiber glass-filled ABS comprising (a) forming a long glass fiber master-batch by adding a long glass fiber to a high flow styrene-acrylonitrile (SAN) copolymer and (b) blending the master-batch with neat mass ABS resin. A molded article demonstrating high dimensional stability, good impact, strength and heat performance is obtained.